

Mid-infrared resonant laser swelling of biocompatible polymers

Gorevoy A.V.^{1,2,®}, Smirnov N.A.^{1,2}, Paholchuk P.P.^{1,2}, Rimskaya E.N.^{1,2}, Gulina Yu.S.^{1,2}, Zhu J.¹ and Kudryashov S.I.^{1,2}

¹ Lebedev Physical Institute of the Russian Academy of Sciences, Leninsky Avenue 53, Moscow, 119991, Russia

² Bauman Moscow State Technical University, 2nd Baumanskaya Street 5, Moscow, 105005, Russia

® a.gorevoy@lebedev.ru

Laser swelling is based on the local expansion of polymers irradiated with laser intensities below the ablation threshold, allowing for surface shaping while maintaining optical-quality roughness without post-processing such as wet etching. We used resonant (C–H bonds stretching) near-surface absorption of mid-infrared (3.2–3.5 μm) laser pulses in biocompatible polymers (polymethylmethacrylate, polydimethylsiloxane, hydrophobic acrylic) to form smooth transparent convex (gaussian-like profile) and flat-top tracks with 7–100 μm width (FWHM) and up to 2.7 μm height (top-view phase change about 12 rad at 633 nm) following freeform trajectories on the surface of the sample and confirmed the technological potential of the method by writing a 20 μm -period sinusoidal phase diffraction grating. The onset of swelling was related to reaching the glass transition temperature in the center of a 5–10 times wider laser-heated material redistribution zone, also characterized by a permanently reduced refractive index and the absence of chemical changes detected by Raman microspectroscopy. The technique is perspective for precise manufacturing of dye-free biocompatible polymer phase micro-optic elements including intraocular lenses, flat optics, compound eyes, and other microimaging systems.

The results have been obtained as a part of the implementation of state assignment No. FSN-2024-0018.